



REF : CUVR 2018/12

ACL-Coat UVR

DESCRIPTION

ACL-Coat UVR is a high grade, two-pack, hard wearing solvent based polyurethane floor coating designed for maximum chemical resistance which is light-fast and flexible. ACL-Coat UVR has good resistance to impact abrasion and trafficking. The system is resistant to a range of temperatures and is available in a range of Colours or Clear. ACL-Coat UVR is regularly used in the Aviation Industry as it has superb resistance to Skydrol, and also used as a sealer to decorative flake systems.

ADVANTAGES

- Excellent chemical resistance
- UV stable, will not discolour
- Some flexibility
- Good abrasion and impact resistance
- Ease of cleaning , including removal of graffiti
- Anti-slip finishes can be created by applying a scatter of aggregate
- Excellent resistance to thermal shock and hot water
- Available in a range of attractive colours

RECOMMENDED USES

- Aircraft hangars
- Laboratories
- Chemical plants
- Prisons and police cells
- Operating theatres
- Schools
- Pharmaceutical areas
- Toilets

PRODUCT INFORMATION

System thickness (dry)	Solids content by weight	Pack sizes	Pack make up	Shelf life	Storage
60 microns (Per coat)	67 %	2.5 litres & 5 litres	1 X Base 1 X Hardener	12 months in sealed containers	Keep out of direct sunlight. Store in a dry place, not below 15°C

DRYING TIMES & COVERAGE RATES at 20°C

Coverage rate	Pot life	Recoat time	Light traffic	Full traffic	Full chemical cure
2.5 litre - 20 sq m 5 litre - 40 sq m @ 60 microns	40 minutes after mixing	6 hours or once surface has lost tackiness	24 Hours	3 Days	7 days

Specification

Product : ACL-Coat UVR

Finish : Gloss

Thickness : 60 microns

Colour : Clear or see ACL PU coating colour chart

Products required for this system

Prime : ACL-Coat HB

System : ACL-Coat UVR

Surface Seal : N/A

Preparation

New Floors: New concrete must be clean, sound, dry and fully cured and surface laitence removed, preferably by shot blasting, mechanical abrasion or chemical etching. Moisture content should be checked prior to application. Do not apply to substrates with moisture readings of 75 % RH or above. If substrates do have higher moisture levels. Prime the substrate with **ACL-Prime DPM** (number of coats dependent on moisture content).

Existing Floors: Remove all dirt, oil, grease or other surface contaminants, preferably by shot blasting, scarification or mechanical planing, Fats, oils or greases must be removed by mechanical abrasion and detergent washing.

All local repairs should be carried out using **ACL-Patch and Fill** or similar.

Priming

Porous substrates such as concrete should be primed with **ACL-Prime** and **ACL Coat HB**.

Application

The ambient temperatures of the areas should not be allowed to fall below 10°C throughout the application and the curing period, as this could have an adverse effect on the appearance and colour of the system. Surface temperature must be above 5°C.

Where possible it is recommended that the application area is heat-ed to a minimum temperature of 15°C to allow the ambient and substrate temperature to stabilise prior to installation. Good ventilation is required along with suitable masks in enclosed areas as this is a solvent based product.

Mixing: Pre-mix the base component to a uniform colour then mix the entire contents of the base with the hardener. If a separate mixing bucket is being used mix thoroughly ensuring all contents of both components are removed from the buckets supplied. Mix using a slow speed electric mixer for approximately two minutes or until the two components have fully combined.

The mixed unit should be applied immediately by roller or brush with a consistent procedure. Floor areas should be cross-rolled to ensure even application and to minimise roller marks.

Coverage rates will depend on porosity of the substrate.

Category Guide

FeRFA Category : 2

Technical Information

The following figures are obtained from laboratory tests and our experience with this product .

Slip Resistance	Dry	> 60
Method BS7976 pt1-3 2002	Wet	Please consult ACL

The slip resistance of a floor surface can vary as a result of the installation process, conditions at the time of application and subsequent traffic. Inappropriate cleaning or maintenance can adversely affect the performance. For further advice on potential wet areas please consult ACL.

Abrasion Resistance	n/a
Method BS8204 /ASTM D4060	

Temperature Resistance	Tolerant of sustained temperatures of up to 150°C
	Excellent.
	Consult ACL for further details

Chemical Resistance	
Compressive Strength	n/a
Flexural Strength	n/a
Tensile Strength	n/a
VOC	453g/l
	Calculation based on a full mixed unit
Life Expectancy	4 years plus
	Subjected to Industrial Traffic
	ACL terms and conditions will apply

Maintenance and Cleaning

ACL recommend that **ACL-Coat UVR** should be cleaned with a regular industrial cleaning regime with a floor scrubber utilising **ACL Industrial Floor Cleaner** or similar with dirty water being removed. Isolated localised cleaning can be car-ried out using **ACL Tyre Mark Remover, ACL Fats and Grease Remover & ACL Oil Remover**. All surfaces should be thoroughly rinsed with clean water after the use of chemical cleaners.

Please refer to the **ACL Guide to Cleaning of Resin Floors**

Health and Safety

ACL-Coat UVR is formulated from materials designed to achieve the highest level of performance as safely as possible. However, specific components require prop-er handling and suitable equipment, this information is given in the relevant safety data sheets. In all cases, spillages or skin contamination should be cleaned as soon as practically possible, by dry wiping of the affected area, and thorough washing with soap and water.

The information given in this data sheet is derived from tests and experience with the products and is believed to be reliable. The information is offered with-out guarantee to enable purchasers to determine for themselves the suitability of the product for their particular application. Any specification or advice given by Resin Surfaces Limited or its agents is based on the information sup-plied by the purchaser. Resin Surfaces Limited cannot be held accountable for errors or omissions as a result of that information being incorrect or in-complete. No undertakings can be given against infringement of patents. Some materials are derived from natural sources. As such some variation may occur. Site conditions may also contribute to variation in finish and colour.